



PYESBR-BOND

Multi Purpose Latex Admixture

DESCRIPTION

PYESBR-BOND is a specially formulated Styrene – Butadiene Polymer multi purpose bonding agent to improve adhesion for various interior and exterior building application areas include swimming pools.

SUITABLE FOR

PYESBR-BOND is designed for priming, acts as bonding agent or modifier for cement sand admixtures provide a damp resistant layer.

DIRECTIONS FOR USE

Application

Priming: Seals off dusty surfaces and acts as a primer prior to fixing of ceramic tiles vinyl or other tiles thus become water resistant layer.

Bonding agent for modifier

Bonding aid for cement sand mortar onto concrete surface or other surfaces. Modify the cement sand mortar in replacement of water for better adhesion, tensile strength, reduce drying shrinkage & better workability.

Admixture

When mix with cement sand as a render / screed mix its increase the adhesion, better workability, flexural strength and thereby reduces the drying shrinkage and gradually become water resistant.

Mixing

Tiling: Mix 1 pail of **PYESBR BOND** to 3 part of cement based adhesive by weight to achieve a workability mortar mix to use for laying floor or wall tiles.

Primer: Mix of **PYESBR BOND** with 1:1 cement sand as a primer coat for building board, slurry bonding coat, damp resistant layer, and use as patch repair etc.

Installation

- i. We do recommend the ceramic tiles to be soaked into water and it must be dry when fixing.
- ii. Apply adhesive at thickness of 3-6mm for spreading no more than 1sq.meter and using a solid bed notched trowels.
- iii. Immediately press tiles firmly into position with a twisting action.



Product Code : BUSB

- iv. After spreading the adhesive, app.15 minutes is allowed, that depends on porosity of background and surrounding condition. If there is a skin formed, re-trowel the adhesive to break the skin.

NOTE: It is very important to determine all the surface condition and suitability prior to the application by the users.

PRODUCT CHARACTERISTICS

Colour	White
Form	Milky liquid
Odour	Pleasant sweet smell.
Adhesion	Increases compressive, bond and flexural strength of concrete to steel.
Drying time	30 mins - 1 hour
Coverage	250 ml PYESBR-BOND in 50 kg cement/sand mix will cover approx. 15.5sq. m. at 6 mm thickness.
Shrinkage	Will not shrink or crack when used in accordance with instructions.
Safety	Non-flammable and can be used in all environments.
Cleaning	Clean tools and equipment with water when wet.

PACKING

4lit, 20lit & 210lit

All information contained within this brochure is only intended to give a fair description of the products and their capabilities under specific test conditions. However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.