



PRIMERO PRO FLEXIBLE CEMENTITIOUS WATERPROOFING SLURRY

PRODUCT DESCRIPTION

Primero Pro Flexible Cementitious Waterproofing Slurry is a two component product that when mixed together, forms a thick, spreadable slurry to waterproof bathrooms, balconies, plant boxes, gutters and roof decks.

SUITABLE FOR

Bathroom floors and walls
Basements
Cement gutters
Balconies
Kitchen floors
Roof decks
Water tanks

SIZES AVAILABLE

22.5 kg set (A – 18 kg powder / B – 4.5 kg liquid)
5 kg set (A – 4 kg powder / B – 1 liter liquid)

COVERAGE

5 kg = 5-6 sq. meters (1 coat)
2.5-3 sq. meters (2 coats)

22.5 kg = 20-22 sq. meters (1 coat)
10-12 sq. meter (2 coats)

DIRECTION OF USE

SURFACE PREPARATION

Surfaces must be clean and free from standing water. Remove any grease, dirt, dust and loose material. Ensure that surface is sound. Hack off cement droppings and repair honeycombs using aqua plug or fast setting cement.

MIXING

Open dry powder (part A) into a clean container. Pour all of liquid (part B) into cement powder mixture. Let soak for 2 minutes and mix well, preferably using an electric mixer to form a slurry like consistency. Ensure that there are no lumps present. Pot life is 2 to 3 hours depending on temperature and weather conditions.



TECHNICAL AND PHYSICAL DATA

Color: Natural Cement

Form: Part A – powder / Part B – liquid

Solids: Cement and high grade silica

Admixture: High strength acrylic polymers

Pot life: 2-3 hours

Thickness: 2-3mm

Coverage: Approx. 1.3 kg/m² for bathroom, terrace, balconies and ext. Approx. 2 kg/m² as protective coating.

Health and Safety: Non-hazardous, non-flammable, non-toxic

Storage: Store in a dry cool place.

Standard: Complies with SIRIM: ASTM D 4541 Pull-off strength of coating using portable adhesion – In house method – Water absorption (Spot test)

Cleaning: Clean tools with water, if hardened remove mechanically.

APPLICATION

Use a trowel, a stiff or Tampico brush. Apply first coat while surface is damp. If surface is dry, spray water to dampen. You may pre-stripe corners and edges, as well as areas with visible cracks. Apply first coat horizontally. Let dry for 2 to 3 hours. Apply second coat vertically. The coats should have a thickness of 1 to 2mm.

PRECAUTIONS

Do not take internally.

Keep out of reach of children.

Store in room temperature.

Keep away from direct sunlight and sources of heat.

Keep container closed when not in use.